

INDION® MB 115

Description

INDION MB 115 is a mixed bed ion exchange resin. It is a mixture of highly purified and super regenerated strong acid cation and strong base anion resins in 40 : 60 volume ratio.

Applications

INDION MB 115 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

Characteristics

Physical

| | | |
|-------------------------|---|---------------------------------------|
| Appearance | : | Spherical beads |
| Shipping weight * | : | 710 kg/m ³ , approximately |
| Particle size range | : | 0.3 to 1.2 mm |
| > 1.2 mm | : | 5.0 %, maximum |
| < 0.3 mm | : | 1 %, maximum |
| Uniformity co-efficient | : | 1.8, maximum |
| Effective size | : | 0.45 to 0.55 mm |
| Microscopic examination | : | Surface cracks not more than 5 % |

Chemical

| | |
|---------------------------|-------------------------|
| Matrix | Crosslinked polystyrene |
| Type | Gel |
| Functional group | Sulphonic acid |
| Total exchange capacity | 1.9 meq/ml |
| Ionic conversion | 99 % minimum in Cl form |
| Moisture holding capacity | 48 - 58 % |
| Thermal stability | Up to 120° C |

Cation resin

| | |
|---------------------------|-------------------------|
| Matrix | Crosslinked polystyrene |
| Type | Gel |
| Functional group | Sulphonic acid |
| Total exchange capacity | 1.9 meq/ml |
| Ionic conversion | 99 % minimum in Cl form |
| Moisture holding capacity | 48 - 58 % |
| Thermal stability | Up to 120° C |

Anion resin

| | |
|---------------------------|-------------------------|
| Matrix | Crosslinked polystyrene |
| Type | Gel |
| Functional group | Quaternary ammonium |
| Total exchange capacity | 1.0 meq/ml |
| Ionic conversion | 90 % minimum in OH form |
| Moisture holding capacity | 60 % maximum |
| Thermal stability | Up to 60° C |

| | | |
|-----------------------|---|---|
| Chemical stability | : | Stable in pH range 0 - 14 Resistant to oxidizing and reducing agents |
| Rinse characteristics | : | MB resins for ultra pure water applications are rinsed with ≥ 17.0 Megaohm.cm water to meet stringent quality requirements. |

* Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Variants

IINDION MB 115 resin is also available with the additional feature of colour change at exhaustion. Three variants of this colour indicating Indion MB 115 are available :

Indion MB 115 (GVI) Green to Violet

Indion MB 115 (BYI) Blue to Yellow

Indion MB 115 (GOI) Green to Orange

Packing

| | |
|--------------------------------|--------------------------|
| PVC Jars with inner liner bags | 5 / 6 lts |
| LDPE lined bags | 0.5 cft / 1 cft / 25 lts |
| HDPE lined bags | 25 / 50 lts |
| HDPE drums | 50 / 100 / 180 lts |

Storage

Ion exchange resins require proper care at all times. Resins must never be allowed to become dry. Resins should therefore be always kept in the shade. Since INDION MB 115 is supplied in highly regenerated condition, any exposure to atmospheric air must be avoided as this will convert it to the carbonate form. The resin packing should not be opened during storage.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.



CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909/3047 2400 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- Chennai - Tel: 044-3989 0909/3910 2900 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- Delhi - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- Kolkata - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- Vashi - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

BRANCH OFFICES

- Bengaluru - Tel: 080-2204 2888
E-mail: bngcro@ionexchange.co.in
- Bhubaneswar - Tel: 0674-326 9525
E-mail: bbsr@ionexchange.co.in
- Chandigarh - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- Hyderabad - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydcro@ionexchange.co.in
- Lucknow - Tel: 0522-301 3401/02 Fax: 0522- 301 3401
E-mail: luk.general@ionexchange.co.in
- Vadodara - Tel: 0265-302 7489/90 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- Visakhapatnam - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES : Ankleshwar • Hosur • Patancheru • Rabale • Verna
ALL INDIA SERVICE AND DEALER NETWORK